

EMAUR®

EMAUR 1K

Descriere:	Produsele EMAUR 1K sunt produse de acoperire pe baza de rasini alchidice, solventi organici, sicativi, adjuvanti, pigmenti. Se caracterizeaza prin: – adeziune excelenta la metal; – rezistenta excelenta la saruri, coroziune alcalina, apa dulce; – rezistenta buna la stropiri cu petrol, uleiuri lubrifiante, uleiuri vegetale ; – ucare rapida ; – buna etalare ; – buna rezistenta la intemperii; – excelenta rezistenta la lumina .	
Produse:	EMAUR 1K EMAUR 1K DILUANT D5065	
Structura de baza:	EMAUR 1K EMAUR 1K DILUANT D5065	rasini alchidice solventi
Tipuri substrat:	EMAUR GRUND	
Raport amestec:	100% vol. EMAUR 1K 10 – 30% vol. EMAUR 1K DILUANT D5065	 100% vol. EMAUR 1K 10 - 30% vol. EMAUR 1K DILUANT D5065
Vascozitatea de aplicare:	20 - 25 s (DIN 4 la 20°C)	 20 - 25 s (DIN 4 la 20°C)
Tipul pistolului de vopsit si presiunea de lucru :	Tip pistol Presiune de lucru RP: 1.3 – 1.4 2.5 - 3.5 bar Conventional: 1.2 – 1.3 2 – 3.5 bar (vezi instructiuni producator)	 RP 1.3-1.4 2.5 -3.5 bar Conventional: 1.2 – 1.3 2 – 3.5 bar

EMAUR®

EMAUR 1K

Aplicare:	Aplicati 2 - 3 straturi pline, (functie de puterea de acoperire), lasand timp de aerare intre straturi 5 – 10 min. In cazul uscarii fortate se lasa un timp de zvantare de 7 -10 minute inainte de introducerea in cuptor.	
Grosime film:	50 - 80 µm	
Consumul de material:	Luand in calcul o eficienta de transfer de 70%, consumul teoretic este de 80 – 120 g / m ² strat. Nota: Pierderile de material in cursul prepararii si aplicarii, variaza si trebuie luate in considerare suplimentar. Acestea depind de metoda de aplicare, forma, marimea si felul suprafetei vopsite.	
Curatirea echipamentului:	Se curata intreg echipamentul cu diluant nitro imediat dupa utilizare.	
Uscare:	24 ore la 20° C 40 min. la 60° C	 24 ore la 20° C 40 min. la 60° C
VOC:	Teoretic VOC: max 600 g/l amestec gata de vopsit	
Termen de valabilitate:	EMAUR 1K	36 luni
Ambalare:	EMAUR 1K	Cutii metalice 1L
Masuri SSM si SU:	Doar pentru uz profesional.(Vezi fisa de securitate). Toate operatiile de manipulare, transport, depozitare, utilizare, distrugere a reziduurilor se vor face aplicand cu strictete normele SU, normele de SSM, in functie de caracterizarea produsului.	